

TITLE

SUPPRESSION OF REPELLENCY IN POLYOLEFINS

ABSTRACT

5 A method for temporarily suppressing repellency of an extruded or
molded object, said object comprising a mixture of a polyolefin and a
fluorocarbon/hydrocarbon ester, by heating the object to a temperature
above 40°C, holding for at least 10 seconds, and cooling is disclosed.

10